



Centro Tessile Serico Sostenibile Srl
 via Castelnuovo, 3 - 22100 Como Italia
 Pho +39 031 3312111/120 Fax: +39 0313312149
 Amministrazione/Contabilità +39 031 3312102-154
 P. IVA - C.F. 003900470133
 Capitale sociale euro 600000,00 iv
 mailbox@textilecomo.com
 www.textilecomo.com



LAB N° 0045 L

Test Report No.:	2006501-001	Customer Code 05485
Date Test Report	02-nov-20	Dear:
Acceptance:	2006501	MARIO SIRTORI SPA
Arrival date sample	29-ott-20	via Papa Giovanni XXIII 10
Start date test	29-ott-20	23845 COSTA MASNAGA (LC) Italia
End date test	02-nov-20	C.a. sig. Sergio Sala Crist
References:		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	

[C] Item:	CARNIVAL
[C] Declared Composition:	40% Cotton - 22% Acrylic - 16% Viscose - 11% Wool - 11% Polyester
[C] End use:	Furnishing
[C] Typology:	Fabric
Return:	No requested

Test Results

Test	Method	U.M.	Result
15066 UPHOLSTERY FURNITURE COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE	UNI EN 1021-1:2014		.
Instrument: Small Test Rig			
Test carried out on			cover fabric
Pretreatment carried out			.
sample wasn't submitted to any pretreatment because it wasn't chemically treated with flame retardant			
Ignition source			source 0 (SMOULDERING CIGARETTE)
Materials of test assembly			
Upholstery filling: fire retardant polyurethane foam with a density of 35 kg/m ³			
Inner cover: -			
Outer cover: SEE ARTICLE DESCRIPTION			
TEST RESULT			SAMPLE PASSE THE TEST
Deviations from the method			none
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2006501-001**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Annex n. 1F to test report n. 2006501-001

DETAILS OF TEST RESULTS

Test executed according to UNI EN 1021-1:2014 (EN 1021-1:2014)

Furniture

Assessment of the ignitability of upholstered furniture

Part 1: Ignition source: smouldering cigarette

Article description: **CARNIVAL**

Declared composition: **40% Cotton - 22% Acrylic - 16% Viscose - 11% Wool - 11% Polyester**

Materials of test assembly:

Upholstery filling: **fire-retardant polyurethane foam with a density of 35 kg/m³**

Inner cover: -

Outer cover: **see article description**

Conditioning of test specimen: **23 ± 2 °C, 50 ± 5 % r.h.**

Testing temperature and r.h.: **19°C, 55% r.h.**

Sample pre-treatment: **sample wasn't submitted to any pretreatment because it wasn't chemically treated with flame retardant**

Date of test: **02.11.2020**

SMOULDERING CRITERIA:	first cigarette	second cigarette	Third cigarette	Comments
Smouldering criteria:				
Unsafe escalating combustion	NO	NO	NO	-
Test assembly consumed	NO	NO	NO	-
Smoulders to extremities	NO	NO	NO	-
Smoulders through thickness	NO	NO	NO	-
Smoulders more than 1 h	NO	NO	NO	Time elapsed between placing the cigarette and extinguishing 1 st 18 min (partial combustion) 2 nd 27 min 3 th 31 min
In final examination, presence of active smouldering	NO	NO	NO	-
Flaming criteria:				
Evidence of flames	NO	NO	NO	

YES = criteria observed

NO = criteria not observed


TEST RESULT: SAMPLE PASSES THE TEST - NON IGNITION

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the material in use.

The probability that the observation criteria mentioned represent the true is equal to 95%.

The expanded uncertainty is calculated by multiplying the combined standard uncertainty for a coverage factor K = 2, which for a normal distribution leads to a confidence level of approximately 95%.

The Laboratory Manager
Fausto Albano





Centro Tessile Serico Sostenibile Srl
 via Castelnuovo, 3 - 22100 Como Italia
 Pho +39 031 3312111/120 Fax: +39 0313312149
 Amministrazione/Contabilità +39 031 3312102-154
 P. IVA - C.F. 003900470133
 Capitale sociale euro 600000,00 iv
 mailbox@textilecomo.com
 www.textilecomo.com



LAB N° 0045 L

Test Report No.:	2006501-002	Customer Code 05485
Date Test Report	02-nov-20	Dear:
Acceptance:	2006501	MARIO SIRTORI SPA
Arrival date sample	29-ott-20	via Papa Giovanni XXIII 10
Start date test	29-ott-20	23845 COSTA MASNAGA (LC) Italia
End date test	02-nov-20	C.a. sig. Sergio Sala Crist
References:		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	

[C] Item:	CARNIVAL
[C] Declared Composition:	40% Cotton - 22% Acrylic - 16% Viscose - 11% Wool - 11% Polyester
[C] End use:	Furnishing
[C] Typology:	Fabric
Return:	No requested

Test Results

Test	Method	U.M.	Result
15076 UPHOLSTERY FURNITURE: ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME	UNI EN 1021-2:2014		.
Instrument: Small Test Rig and burner			
Test carried out on			COVER FABRIC
Pretreatment carried out			.
sample wasn't submitted to any pretreatment because it wasn't chemically treated with flame retardant			
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
Materials of test assembly			.
Upholstery filling: fire retardant polyurethane foam with a density of 35 kg/m ³ Inner cover: - Outer cover: SEE ARTICLE DESCRIPTION			
TEST RESULT			SAMPLE PASSES THE TEST
Deviations from the method			none
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2006501-002**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
 Via Castelnuovo, 3 – 22100 Como Italia
 Tel. +39 031331211/120 Fax +39 031 3312149
 Amministrazione/Contabilità +39 031 3312102-154
 P.IVA – C.F. 03900470133
 Capitale sociale euro 600.000,00 iv
 mailbox@textilecomo.com
 www.textilecomo.com



LAB N° 0045 L

Annex n. 1F to test report n. 2006501-002

DETAILS OF TEST RESULTS

Test executed according to UNI EN 1021-2:2014 (EN 1021-1:2014) Furniture - Assessment of the ignitability of upholstered furniture Part 2: Ignition source: match flame equivalent

Article description: **CARNIVAL**

Declared composition: **40% Cotton - 22% Acrylic - 16% Viscose - 11% Wool - 11% Polyester**

Materials of test assembly:

Upholstery filling: **fire-retardant polyurethane foam with a density of 35 kg/m³**

Inner cover: -

Outer cover: **see article description**

Conditioning of test specimen: **23 ± 2 °C, 50 ± 5 % r.h.**

Testing temperature and r.h.: **19°C – 57% r.h.**

Sample pre-treatment: **sample wasn't submitted to any pretreatment because it wasn't chemically treated with flame retardant**

Date of test: **02.11.2020**

SMOULDERING CRITERIA:	1st test	2nd test	3rd test	Comments
Smouldering criteria:				
Unsafe escalating combustion	NO	NO	NO	Time smouldering: 1st test: 5 s 2nd test: 6 s 3rd test: 6 s
Test assembly consumed	NO	NO	NO	
Smoulders to extremities	NO	NO	NO	
Smoulders through thickness	NO	NO	NO	
Smoulders more than 1 hour	NO	NO	NO	
In final examination, presence of active smouldering	NO	NO	NO	
Flaming criteria:				
Unsafe escalating combustion	NO	NO	NO	Time flaming: 1st test: 2 s 2nd test: 2 s 3rd test: 2 s
Test assembly consumed	NO	NO	NO	
Flames to extremities	NO	NO	NO	
Flames through thickness	NO	NO	NO	
Flames more than 120 s	NO	NO	NO	

YES = criteria observed

NO = criteria not observed

TEST RESULT: SAMPLE PASSES THE TEST – NON IGNITION

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test.

They are not intended as a means of assessing the full potential fire hazard of the material in use.

The probability that the observation criteria mentioned represent the truth is equal to 95%.

The expanded uncertainty is calculated by multiplying the combined standard uncertainty for a coverage factor K = 2, which for a normal distribution leads to a confidence level of approximately 95%.

The Laboratory Manager
 Fausto Albonico