



**Centro Tessile Serico Spa consortile**  
Via Castelnuovo, 3 - 22100 Como, Italia  
Tel. +39 031 331211-120 Fax +39 031 3312180  
Amministrazione/Contabilità  
Tel. +39 0313312102-154  
P.IVA - C.F. 02381270137  
Capitale sociale euro 552.693,18 i.v.  
mailbox@textilecomo.com  
www.textilecomo.com



LAB n° 0045

## TEST REPORT

Report nr.: **1803145-004**  
Report date: **22-giu-18**  
Acceptance code: **1803145**  
Acceptance date: **08-giu-18**  
Start test date: **08-giu-18**  
End test date: **22-giu-18**  
References: ---

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer  
Article description: **LINVIRA CS**  
Declared composition: **100% Trevira**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **Specimens enclosed**

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>14063-ABRASION RESISTANCE (Martindale method): SPECIMENS BREAKDOWN</b>		-
<b>Method:</b> UNI EN ISO 12947-2:2017		
<b>Instrument:</b> Abrasion Tester Martindale		
<b>SPECIMEN BREAKDOWN (END POINT):</b> The breakdown point of the specimen is reached when: -Woven fabric (without pile): Two threads completely broken -Knitted fabric (without pile): One thread completely broken -Cut pile woven fabric: Two threads completely broken -Cut pile knitted fabric: One thread completely broken -Woven pile fabric with chenille yarns: Two threads completely broken -Knitted pile fabric with chenille yarns: One thread completely broken -Woven uncut pile fabric: Two threads completely broken -Knitted uncut pile fabric: One thread completely broken -Woven raised fabric: Two threads completely broken -Knitted raised fabric: One thread completely broken -Flocked fabrics: tested area completely worn off -Non-woven fabrics: surface layer shows a worn of diameter 2,5 mm		
Date of test:		11-06-2018
Pretreatment carried out		no one
First specimen: cycles to end point	cycles	50000
Second specimen: cycles to end point	cycles	50000
Third specimen: cycles to end point	cycles	60000
QUOTED RESULT: the lowest individual value	cycles	50000
Change of appearance: fuzzing formation is observed.		

(\*) = the tests marked with asterisk are not accredited by Accredia.



**Centro Tessile Serico Spa consortile**  
Via Castelnuovo, 3 - 22100 Como, Italia  
Tel. +39 031 331211-120 Fax +39 031 3312180  
Amministrazione/Contabilità  
Tel. +39 0313312102-154  
P.IVA - C.F. 02381270137  
Capitale sociale euro 552.693,18 i.v.  
mailbox@textilecomo.com  
www.textilecomo.com



LAB n° 0045

Report nr.

**1803145-004**

TEST	M.U.	RESULTS
Load applied	kPa	12
Change in colour	grade	Not requested
Deviation from procedure		-
Enclosed:	nr.	1

----- **END OF TEST REPORT** -----

**Technical Head**

Enrica Baldini

(\*) = the tests marked with asterisk are not accredited by Accredia.