



REPORT

Report nr.: **1600361-001**
 Report date: **03-feb-16**
 Acceptance code: **1600361**
 Acceptance date: **21-gen-16**
 Start test date: **21-gen-16**
 End test date: **03-feb-16**
 References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
 sig. Sergio Sala Crist
 Tel.nr: +39 031 879632
 Fax.nr.: +39 031 855397

Article description: **TUNDRA 01**
 Declared composition: **42% Viscose - 36% Cotton - 16% Acrylic - 6% Polyester**
 End use: **Furnishing**
 Typology: **Fabric**
 Return: **Specimens enclosed**
 Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
 This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14063 RESISTANCE TO ABRASION (Martindale) - DETERMINATION OF SPECIMEN BREAKDOWN		
Method:	UNI EN ISO 12947-2:2000 + EC 1-2010	
Instrument:	Abrasion Tester Martindale J.Heal - 103	
SPECIMEN BREAKDOWN		
Specimen breakdown is reached when:		
- in woven fabric, when two separate threads are completely broken;		
- in knitted fabric, when one thread is broken causing a hole;		
- in pile fabric, when the pile is fully worn off;		
- in nonwoven fabric, when the first hole is of a diameter at least equal to 0,5 mm.		
Date of test:		26-01-2016
Pretreatment carried out		NO ONE
First specimen: cycles to end point	cycles	28000
Second specimen: cycles to end point	cycles	30000
Third specimen: cycles to end point	cycles	34000
Average	cycles	30667
Confidence limits		-
Load applied	kPa	12
Change in colour at the end point (when stated)	grade	4-5
Pilling occurred	cycles	-
Deviation from procedure		-
Enclosed:	nr.	1



Report nr.

1600361-001

END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu