



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com  
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	<b>2205500-004</b>	Customer Code 05485
Date Test Report	<b>19-lug-22</b>	Dear:
Acceptance:	<b>2205500</b>	<b>MARIO SIRTORI SPA</b>
Arrival date sample	<b>14-lug-22</b>	via Papa Giovanni XXIII 10
Start date test	<b>14-lug-22</b>	23845 COSTA MASNAGA (LC) Italia
End date test	<b>18-lug-22</b>	C.a. sig. Sergio Sala Crist
References:		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	

[C] Item:	<b>RICCIOLONE</b>
[C] Declared Composition:	<b>56% Acrylic - 15% Polyester - 12% Viscose - 11% Cotton - 6% Flax</b>
[C] End use:	<b>furnishing</b>
[C] Typology:	<b>fabric</b>
Return:	<b>no requested</b>

### Test Results

Test	Method	U.M.	Result
<b>15066 UPHOLSTERY FURNITURE</b> <b>COMPONENTS: ASSESSMENT OF THE</b> <b>IGNITABILITY BY SMOULDERING CIGARETTE</b>	<b>UNI EN 1021-1:2014</b>		.
Start date test	15/07/2022		
End date test	18/07/2022		
Instrument:	Mini Mock Up Tester		
Test carried out on			COVER FABRIC
Pretreatment carried out			No one
sample was not submitted to any pretreatment because it was not chemically treated with flame retardant.			
Testing temperature and r.h.			25°C - 61% U.R
Ignition source			source 0 (SMOULDERING CIGARETTE)
Materials of test assembly			.
Upholstery filling: fire retardant polyurethane foam with a density of 35kg/m <sup>3</sup>			
Inner cover: -			
Outer cover: SEE ARTICLE DESCRIPTION			
TEST RESULT			<b>SAMPLE PASSES THE TEST:</b> <b>NON IGNITION</b>
Note: to assess the ignitability of this sample, the test has been carried out using a fire-retardant polyurethane foam with a density of 35 kg/m <sup>3</sup> as filling of the upholstered seating. The test result could be different using another type of filling material.			
Deviations from the method			No one
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2205500-004**

Test	Method	U.M.	Result
------	--------	------	--------

**The Laboratory Manager**

Fausto Albonico

-----  
**END OF REPORT**  
-----

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
 Via Castelnuovo, 3 – 22100 Como Italia  
 Tel. +39 031331211 Fax +39 0313312149  
 Amministrazione/Contabilità +39 0313312102-154  
 P.IVA – C.F. 03900470133  
 Capitale sociale euro 600.000,00 iv  
[mailbox@textilecomo.com](mailto:mailbox@textilecomo.com)  
[www.textilecomo.com](http://www.textilecomo.com)



LAB N° 0045 L

Annex n. 1F to test report n. 2205500-004

## DETAILS OF TEST RESULTS

### Test executed according to UNI EN 1021-1:2014 (EN 1021-1:2014) Furniture - Assessment of the ignitability of upholstered furniture Part 1: Ignition source: smouldering cigarette

Article description: **RICCIOLONE**

Declared composition: **56% Acrylic – 15% Polyester – 12% Viscose – 11% Cotton – 6% Flax**

Materials of test assembly:

Upholstery filling: **fire-retardant polyurethane foam with a density of 35 kg/m<sup>3</sup>**

Inner cover: -

Outer cover: **see article description**

Conditioning of test specimen: **23 ± 2 °C, 50 ± 5 % r.h.**

Testing temperature and r.h.: **25°C – 61% U.R. r.h.**

Sample pre-treatment: **sample wasn't submitted to any pretreatment because it wasn't chemically treated with flame retardant**

Date of test: 15/07/2022

<b>SMOULDERING CRITERIA:</b>	<b>1<sup>st</sup> cigarette</b>	<b>2<sup>nd</sup> cigarette</b>	<b>3<sup>rd</sup> cigarette</b>	<b>Comments</b>
<b>Smouldering criteria:</b>				
Unsafe escalating combustion	NO	NO	-	Time elapsed between placing the cigarette and extinguishing 1 <sup>st</sup> 21 min 2 <sup>nd</sup> 23 min
Test assembly consumed	NO	NO	-	
Smoulders to extremities	NO	NO	-	
Smoulders through thickness	NO	NO	-	
Smoulders more than 1 h	NO	NO	-	
In final examination, presence of active smouldering	NO	NO	-	
<b>Flaming criteria:</b>				
Evidence of flames	NO	NO	-	

**YES = criteria observed**

**NO = criteria not observed**

### TEST RESULT: SAMPLE PASSES THE TEST - NON IGNITION

*The above test results relate only to the ignitability of the combination of materials under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the material in use.*

*The probability that the observation criteria mentioned represent the truth is equal to 95%.*

The Laboratory Manager

Fausto Albanico



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com  
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	<b>2205500-005</b>	Customer Code 05485
Date Test Report	<b>19-lug-22</b>	Dear:
Acceptance:	<b>2205500</b>	<b>MARIO SIRTORI SPA</b>
Arrival date sample	<b>14-lug-22</b>	via Papa Giovanni XXIII 10
Start date test	<b>14-lug-22</b>	23845 COSTA MASNAGA (LC) Italia
End date test	<b>18-lug-22</b>	C.a. sig. Sergio Sala Crist
References:		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	

[C] Item:	<b>RICCIOLONE</b>
[C] Declared Composition:	<b>56% Acrylic - 15% Polyester - 12% Viscose - 11% Cotton - 6% Flax</b>
[C] End use:	<b>furnishing</b>
[C] Typology:	<b>fabric</b>
Return:	<b>no requested</b>

### Test Results

Test	Method	U.M.	Result
<b>15076 UPHOLSTERY FURNITURE: ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME</b>	<b>UNI EN 1021-2:2014</b>		.
Start date test	15/07/2022		
End date test	18/07/2022		
Instrument:	Small Test Rig and burner		
Test carried out on			COVER FABRIC
Pretreatment carried out			No one
sample was not submitted to any pretreatment because it was not chemically treated with flame retardant.			
Testing temperature and r.h.			25°C - 61% U.R
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
Materials of test assembly			.
Upholstery filling: fire retardant polyurethane foam with a density of 35kg/m <sup>3</sup>			
Inner cover: -			
Outer cover: SEE ARTICLE DESCRIPTION			
TEST RESULT			SAMPLE PASSES THE TEST: NON IGNITION
Note: to assess the ignitability of this sample, the test has been carried out using a fire-retardant polyurethane foam with a density of 35 kg/m <sup>3</sup> as filling of the upholstered seating. The test result could be different using another type of filling material.			
Deviations from the method			No one

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2205500-005**

Test	Method	U.M.	Result
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

The Laboratory Manager

Fausto Albonico

-----  
**END OF REPORT**  
-----

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
 Via Castelnuovo, 3 – 22100 Como Italia  
 Tel. +39 031331211 Fax +39 0313312149  
 Amministrazione/Contabilità +39 0313312102-154  
 P.IVA – C.F. 03900470133  
 Capitale sociale euro 600.000,00 iv  
[mailbox@textilecomo.com](mailto:mailbox@textilecomo.com)  
[www.textilecomo.com](http://www.textilecomo.com)



LAB N° 0045 L

Annex n. 1F to test report n. 2205500-005

## DETAILS OF TEST RESULTS

### Test executed according to UNI EN 1021-2:2014 (EN 1021-1:2014) **Furniture - Assessment of the ignitability of upholstered furniture** **Part 2: Ignition source: match flame equivalent**

Article description: **RICCIOLONE**

Declared composition: **56% Acrylic – 15% Polyester – 12% Viscose – 11% Cotton – 6% Flax**

Materials of test assembly:

Upholstery filling: **fire-retardant polyurethane foam with a density of 35 kg/m<sup>3</sup>**

Inner cover: -

Outer cover: **see article description**

Conditioning of test specimen: **23 ± 2 °C, 50 ± 5 % r.h.**

Testing temperature and r.h.: **23°C – 50% r.h.**

Sample pre-treatment: **sample wasn't submitted to any pretreatment because it wasn't chemically treated with flame retardant**

Date of test: 15/07/2022

<b>SMOULDERING CRITERIA:</b>	<b>1<sup>st</sup> test</b>	<b>2<sup>nd</sup> test</b>	<b>3<sup>rd</sup> test</b>	<b>Comments</b>
<b>Smouldering criteria:</b>				
Unsafe escalating combustion	NO	NO	NO	Time smouldering: 1st test: 8s 2nd test: 12s 3rd test: 11s
Test assembly consumed	NO	NO	NO	
Smoulders to extremities	NO	NO	NO	
Smoulders through thickness	NO	NO	NO	
Smoulders more than 1 hour	NO	NO	NO	
In final examination, presence of active smouldering	NO	NO	NO	
<b>Flaming criteria:</b>				
Unsafe escalating combustion	NO	NO	NO	Time flaming: 1st test: 0s 2nd test: 1s 3rd test: 1s
Test assembly consumed	NO	NO	NO	
Flames to extremities	NO	NO	NO	
Flames through thickness	NO	NO	NO	
Flames more than 120 s	NO	NO	NO	

**YES = criteria observed**

**NO = criteria not observed**

### TEST RESULT: SAMPLE PASSES THE TEST – NON IGNITION

*The above test results relate only to the ignitability of the combination of materials under the particular conditions of test.*

*They are not intended as a means of assessing the full potential fire hazard of the material in use.*

*The probability that the observation criteria mentioned represent the truth is equal to 95%.*

The Laboratory Manager  
 Fausto Albionico